


SPECIFICATION SHEET

Iconic Ocean

180 to 450 GSM

(ON LINE COATED BOARD) M/C Deckle-365-370cms



Application

1. Packaging board
2. Printing job

Recommended for Multi-color printing

1. Letter press

Substance	Stiffness (Taber)			Caliper	Bulk	Parameters		
gm/m ²	T 489 om-99			Micron	cc/gm.	Roughness - PPS	Microns	3.5±0.5
	MD	CD	GM			T 555 om - 99		
180	20	18	19	218	1.21	Brightness Top	%	73±1
200	32	14	21	242	1.21	T 452 om - 98		
230	50	22	33	278	1.21	Gloss at 75	%	22±3
250	65	29	43	308	1.23	T 480 om - 99		
260	70	32	47	325	1.25	Plybond (scott)	Jules	>100
285	85	37	56	359	1.26	Tappi : T-833		
295/300	105	45	69	366	1.26	IGT Dry Pick	(m/sec)	>0.7
320	125	57	84	403	1.26	ISO 3782		
330	135	60	90	416	1.26	COBB Top	g/m ²	35-50
350	150	72	104	441	1.26	Bottom		50-100
360	165	75	111	454	1.26	T 441 om - 98		
400	190	90	131	508	1.27	Smoothness-Bendtsen	ml/min	100-150
420	210	100	145	533	1.27	ISO-8791-2		
450	290	135	198	572	1.27	Burst Factor	-	15±2
						Tappi T807		
Tolerance						Moisture Content	%	7.5%±1.0%
±3%	±10%			±5%	±5%	Tappi T412 om 02		